

JUL 21 2008

Appl. No. 10/719,897  
Amdt. Dated July 13, 2008  
Reply to Office Action of March 13, 2008

Attorney Docket No. 81707.0190  
Customer No. 26021

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1-8. (Canceled)

9. (Previously presented) A method of producing a multi-layer circuit board by preparing a circuit-parts sheet which comprises a photo-cured ceramic sheet and a circuit-forming pattern through the steps (a) to (e) described below and, then, conducting the steps (f) to (h) described below:

(a) forming the circuit-forming pattern having light-nontransmitting property on a surface of a carrier film having light-transmitting property;

(b) forming a photo-curable ceramic coating layer having a thickness not smaller than the thickness of said circuit-forming pattern and in which said circuit-forming pattern is buried, by applying a photo-curable slurry containing an electrically insulating ceramic material on the surface of the carrier film on which said circuit-forming pattern is formed;

(c) forming a photo-cured ceramic sheet by photo-curing said photo-curable ceramic coating layer which is not present on the circuit-forming pattern by the irradiation with light from the back surface of said carrier film, wherein the photo-curable ceramic coating layer which is present on the circuit-forming pattern is not photo-cured;

(d) removing uncured portions of said photo-curable ceramic coating layer by using a developing solution;

(e) peeling off said carrier film;

Appl. No. 10/719,897  
Amdt. Dated July 13, 2008  
Reply to Office Action of March 13, 2008

Attorney Docket No. 81707.0190  
Customer No. 26021

- (f) preparing a plurality of pieces of the circuit-parts sheets obtained through the steps (a) to (e);
- (g) laminating a plurality of pieces of the circuit-parts sheets; and
- (h) firing the laminate thereof.

10. (Previously presented) A method of producing a multi-layer circuit board by preparing a circuit-parts sheet which comprises a photo-cured ceramic sheet and a circuit-forming pattern through the steps (a) to (d) described below and, then, conducting the steps (e) to (h) described below:

(a) forming the circuit-forming pattern having light-nontransmitting property on a surface of a carrier film having light-transmitting property;

(b) forming a photo-curable ceramic coating layer having a thickness not smaller than the thickness of said circuit-forming pattern and in which said circuit-forming pattern is buried, by applying a photo-curable slurry containing an electrically insulating ceramic material on the surface of the carrier film on which said circuit-forming pattern is formed;

(c) forming a photo-cured ceramic sheet by photo-curing said photo-curable ceramic coating layer which is not present on the circuit-forming pattern by the irradiation with light from the back surface of said carrier film, wherein the photo-curable ceramic coating layer which is present on the circuit-forming pattern is not photo-cured;

(d) removing uncured portions of said photo-curable ceramic coating layer by using a developing solution;

(e) preparing a plurality of pieces of the circuit-parts sheets with the carrier film obtained through the steps (a) to (d);

(f) laminating another circuit-parts sheet with the carrier film on one circuit-parts sheet with the carrier film in a manner that the circuit-parts sheets

Appl. No. 10/719,897  
Amdt. Dated July 13, 2008  
Reply to Office Action of March 13, 2008

Attorney Docket No. 81707.0190  
Customer No. 26021

are opposed to each other, and peeling off the carrier film from the other circuit-parts sheet;

(g) fabricating a laminate having a plurality of pieces of the circuit-parts sheets by repeating the step (f); and

(h) peeling off the carrier film from said one circuit-parts sheet of the obtained laminate, followed by firing.

11. (Original) A method of producing a multi-layer circuit board according to claim 10, wherein both said photo-cured ceramic sheet and said circuit-forming pattern have thicknesses of not larger than 50  $\mu\text{m}$ , and a difference in the thickness between said photo-cured ceramic sheet and the circuit-forming pattern is not larger than 5  $\mu\text{m}$ .

12. (Original) A method of producing a multi-layer circuit board according to claim 10, wherein said circuit-forming pattern is formed by using at least either one of an electrically conducting material or an electrically insulating ceramic material.

13. (Original) A method of producing a multi-layer circuit board according to claim 12, wherein said electrically conducting material contains a metal powder and an organic binder.

14. (Original) A method of producing a multi-layer circuit board according to claim 12, wherein said electrically conducting material is a metal foil.

15. (Previously presented) A method of producing a multi-layer circuit board according to claim 10, wherein said circuit-forming pattern and a thermally extinguishing pattern having a light-non transmitting property are so formed in

Appl. No. 10/719,897  
Amdt. Dated July 13, 2008  
Reply to Office Action of March 13, 2008

Attorney Docket No. 81707.0190  
Customer No. 26021

said step (a) that said circuit-forming pattern and said thermally extinguishing pattern will not be overlapped one upon the other, and the photo-curable ceramic coating layer is so formed in said step (b) that said circuit-forming pattern and said thermally extinguishing pattern are buried therein.

16. (Original) A method of producing a multi-layer circuit board according to claim 15, wherein said thermally extinguishing pattern is formed by using a thermally disintegrating resin composition.

17. (Original) A method of producing a multi-layer circuit board according to claim 10, wherein one surface of said cured ceramic sheet has a maximum surface roughness  $R_{max}$  (JIS B 0601) of not smaller than 1  $\mu m$ , and the laminate is so formed that the roughened surfaces are opposed to each other.

18. (Previously presented) A method of producing a multi-layer circuit board by preparing a circuit-parts sheet which comprises a photo-cured ceramic sheet and a circuit-forming pattern secured to said sheet and is held on a surface of a carrier film having light-transmitting property through the steps (a) to (d) described below and, then, laminating a ceramic green sheet having through-holes filled with a conducting paste on said circuit-parts sheet, and peeling off the carrier film from the obtained laminate, followed by firing:

(a) forming the circuit-forming pattern having light non-transmitting property on the surface of a carrier film having light-transmitting property;

(b) forming a photo-curable ceramic coating layer having a thickness not smaller than the thickness of said circuit-forming pattern and in which said circuit-forming pattern is buried, by applying a photo-curable slurry containing an

Appl. No. 10/719,897  
Amdt. Dated July 13, 2008  
Reply to Office Action of March 13, 2008

Attorney Docket No. 81707.0190  
Customer No. 26021

electrically insulating ceramic material on the surface of the carrier film on which said circuit-forming pattern is formed;

(c) forming a photo-cured ceramic sheet by photo-curing said photo-curable ceramic coating layer which is not present on the circuit-forming pattern by the irradiation with light from the back surface of said carrier film, wherein the photo-curable ceramic coating layer which is present on the circuit-forming pattern is not photo-cured; and

(d) removing uncured portions of said photo-curable ceramic coating layer by using a developing solution.

19-21. (Canceled)